

BRUSHING LACQUER

Description

Old Masters Brushing Lacquer is a crystal clear, fast drying and self-leveling interior lacquer for use on wood surfaces. It provides a durable finish, resistant to water and alcohol. It is easily repaired and recoated without removing the old finish. Fast drying, this formula allows multiple coats and one-day finishing. This is a nitrocellulose lacquer.

Surface Preparation

All surfaces must be clean, dry and free from dirt, wax, grease, glue and other contaminants or penetration and adhesion will be affected.

Bare Wood Surfaces: Sand surface thoroughly with medium grit sandpaper and progress to fine grit sandpaper. Always sand in

Previously Finished Wood: Surface should be sanded to remove imperfections and gloss, using extra fine sandpaper (220 grit), sanding with the grain. Remove dust with a tack rag. Before applying Brushing Lacquer to previously finished surfaces, test on an inconspicuous area. If wrinkling or lifting of the old finish occurs, remove with a wax-free paint remover and refinish as a bare wood surface.

Stained Surfaces: Stain must be thoroughly dry before applying clear finish. Do not sand uncoated stained surfaces.

WARNING! If you scrape, sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Application

Stir thoroughly before and during application. DO NOT SHAKE. For larger projects requiring more than one container, combine containers and mix to ensure gloss uniformity. Test the finish on an inconspicuous area to ensure adequate adhesion. Do not apply in direct sunlight or areas of extreme air movement.

1. Apply with brush, flat pad or spray.
2. Flow on generously with minimum brushing to achieve a glass-like finish. Maintain a wet brush, applying with the grain
3. Brushing Lacquer will dry to touch in 30 minutes. Sanding is not required between coats unless surface feels rough. If necessary, sand with very fine sandpaper and remove dust. Allow 2 hours between coats.
4. Reapply. A minimum of three coats is recommended for ultimate protection. In high moisture areas, apply up to 6 coats to prevent white water spotting. Allow finish to cure for at least 24 hours before subjecting to normal use.

Coverage

Approximately 200 to 300 square feet per gallon. Coverage will vary significantly depending on application method and condition of wood.

Product Codes

Available Sizes: Spray (10), Quart (04) and Gallon (01)

927	Gloss
928	Semi-Gloss
929	Satin

BRUSHING LACQUER

Drying Time

Apply when air and surface temperatures are between 60° and 90°F and humidity is between 30% and 70%. At 50% relative humidity and 70°F, Brushing Lacquer will dry to touch in 30 minutes. Recoat after 2 hours. Dry time will be affected by temperature, humidity and film thickness. Protect product from freezing prior to and during application.

Wait 24 hours before subjecting surfaces to light use. Care should be used during the first week after application as the finish is curing to its ultimate hardness.

Clean Up

Lacquer thinner is recommended for cleanup. The use of lacquer thinner may violate VOC compliancy in your area. Check with your local government agencies to ensure proper compliancy.

DANGER: Rags, steel wool, sanding residue, and other wastes used or soaked with this product may spontaneously catch fire if improperly discarded. No ignition source is required for these wastes to start on fire by themselves. Immediately place rags, steel wool, sanding residue, and other wastes used or soaked with this product in a sealed, water-filled metal container. Dispose of in accordance with local fire regulations.

Limited Warranty

Since Old Masters does not control the application of its products, nor is the condition of the surface to which they are applied, a Limited Warranty is provided. If the products do not perform as specified, for whatever reason, Old Masters liability will under no circumstances exceed the replacement of the product.

Technical Data

Gloss Levels at 60°

Gloss	90+
Semi-Gloss	55 to 65
Satin	25 to 35

Product Information

Solids by Volume	18 to 19%
Solids by Weight	27 to 28%
Weight per Gallon	7.7 to 7.8 lbs
Vehicle	Lacquer
Viscosity at 77°F #2 Zahn	Gloss 20 to 25 secs. Semi-Gloss 20 to 25 secs. Satin 26 to 30 secs.
Flash Point	66°F
Recommended Thinner	Do not thin. Used as packaged.
VOCs	680 g/L

Coverage

Theoretical Coverage @ Mil DFT	300 sq ft/gal
Coverage @ Recommended DFT	150 to 300 sq ft/gal
Recommended DFT Per Coat	1 to 2 mils

Dry Times at 70°F and 50% Humidity

Touch	30 minutes
Recoat	2 hours